

Description

ALCHEMIX PU 3841 is a two component polyurethane system, which is designed to simulate thermoplastics such as polypropylene. The system is ideal for rapid prototyping and limited production runs using dedicated metering machinery. The product is ideal for high temperature applications, such as under the bonnet uses in the automotive industry.

Features

- Fast room temperature cure (20 – 25°C)
- Fast demould
- Excellent impact strength
- High temperature resistance

Mix Ratio

	PU 3841A	PU 3841B
By Weight	100	70
By Volume	100	59

Component Data

	Conditions	PU 3841A	PU 3841B
Description	-	Polyol	Isocyanate
Appearance	-	Black liquid	Brown liquid
Viscosity	25°C	1250 – 1750 mPa.s	180 – 240 mPa.s
Density	25°C	1.00 – 1.05 gcm ⁻³	1.20 – 1.25 gcm ⁻³

Cure Data

	Conditions	Typical Value
Appearance	-	Black
Mixed Viscosity	25°C	550 – 750 mPa.s
Mixed Density	25°C	1.07 – 1.12 gcm ⁻³
Pot Life	200g, 25°C	55 – 65 secs
Demould Time	3mm, 25°C	15 – 25 mins
Maximum Casting Thickness	-	8 mm

Cured Properties

	Standard	Typical Value
Hardness	ISO 868	77 – 82 D
Linear Shrinkage ¹	500 x 50 x 4mm	2 mm/m
Tensile Strength	ISO 527	35 – 40 MPa
Elongation at Break	ISO 527	5.5 – 7.5 %
Tensile Modulus	ISO 527	950 – 1250 MPa
Flexural Strength	ISO 178	43 – 48 MPa
Flexural Modulus	ISO 178	900 – 1200 MPa
Glass Transition Temperature (T _g) ²	DMA	139 – 144 °C

¹ See “Shrinkage” section below.

² T_g will depend on exotherm generated during the reaction.

Mould Preparation

Ensure that the mould is clean and dry and if the mould is made from metal or resin, use a release agent such as Release Agent R7. For flexible moulds, use ALCHEMIX RTV Silicone Rubber. Never use silicone release agents if the units are to be painted.

Resin Preparation

Stir the Part A can thoroughly in order to homogenise the resin. For best results, ensure the two components are at between 20 – 25°C before use.

Processing Instructions

ALCHEMIX PU 3841 should be processed using a suitable low pressure RIM machine. For further information on processing ALCHEMIX PU 3841, or for recommended machinery suppliers, please contact Alchemie Ltd.

Curing

The precise demould time will vary with the casting thickness, as thin section units will cure slower than thicker section units. When casting thin wall sections, ensure that the mould and

resin components are at least 20 – 25°C to facilitate a full cure. Post cure is not usually required for this product.

Shrinkage

The shrinkage value above is quoted as a guide only. Shrinkage will vary with each mould design, as factors such as mould size and geometry can affect the degree of shrinkage. Generally speaking, large, thick castings will have a greater degree of shrinkage than small, thin castings. Other factors, such as mould temperature and resin temperature can also have an effect. Post curing the part can also lead to a greater degree of shrinkage. Please contact Alchemie Ltd for more information.

Storage

ALCHEMIX PU 3841A and B should be stored in original, unopened containers between 20 and 25°C. ALCHEMIX PU 3841B may crystallise partially or completely if not stored at above 20°C. Like all polyurethanes, both components are moisture sensitive. Moisture absorption will cause excessive aeration in cast parts. KEEP THE PACKING TIGHTLY SEALED WHEN NOT IN USE. If stored under the above conditions, ALCHEMIX PU 3841A and B will have a shelf life of 6 months, from the date of production.

Packaging

ALCHEMIX PU 3841A is supplied in 5kg and 25kg kits.
ALCHEMIX PU 3841B is supplied in 3.3kg and 16.5kg kits.
Please contact Alchemie Ltd for bulk supply.

Further Information

This data is not to be used for specifications. Values listed are for typical properties and should not be considered minimum or maximum.

Our technical advice, whether verbal or in writing, is given in good faith, but without warranty. This also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended process and use.

Before using any of our products, users should familiarise themselves with the relevant Technical Data Sheet (TDS) and Safety Data Sheets (SDS) provided by Alchemie Ltd.

Alchemie® and Alchemix® are registered trademarks of Alchemie Ltd.